



PO Box 640, 8730 Rutledge Pike ♦ Rutledge, TN 37861  
 ♦ USA Phone 865-773-0599  
 ♦ Fax 865-773-0599  
[www.techlinecoatings.com](http://www.techlinecoatings.com)

**PRODUCT DATA SHEET Ciloxide™ Black**  
**(CXBK)**

**SELECTION DATA**

**PRODUCT DESCRIPTION:**

**Ciloxide** is a “ceramic” coating designed to be applied primarily to exhaust systems components and other parts subject to high temperature and movement/flexing. When applied to exhaust systems **Ciloxide** will withstand substrate temperatures of over 2000°f. **Ciloxide** will handle environmental temperatures of up to 2000°f. Due to its unique ceramic nature, the coating also functions as a very effective thermal barrier, with reduced thermal radiation characteristics. In addition **Ciloxide** has lubricating/release capabilities. **Ciloxide** may be partially cured at 500°f for one hour; however, a **full cure at 750°F for one hour at temperature is required.** The coating cures out to a durable surface with excellent adhesion. Corrosion and chemical resistance is only achieved after the coating achieves a complete cure.

**NOT RECOMMENDED FOR: N/A**

**CHEMICAL RESISTANCE GUIDE:**

<u>Exposure</u>	<u>Splash &amp; Spillage</u>	<u>Fumes</u>
Acids	Poor	Poor
Alkaline	Poor	Poor
Solvent	Good	Good
Fluids	Good	Good
Fuels	Good	Good
Salt	Good	Good
Water	Good	Good

**TEMPERATURE RESISTANCE:** (non-immersion)  
 2000f substrate, 2000f maximum environmental

**SUBSTRATES:** May be applied to both ferrous and non-ferrous.

**TOPCOAT REQUIRED:** None Required

**COMPATIBILITY WITH OTHER COATINGS:** May be applied over MCS or HHBK to withstand higher substrate temperature or to increase the thermal barrier functions.

**RECOMMENDED DRY FILM THICKNESS PER COAT:**  
 .001” to .0015”

**SURFACE PREPARATION:** All parts must be absolutely free of all oils, grease, moisture, dust, scale or corrosion.

**METALS:** For steel, sandblast with 80-100 grit aluminum oxide or similar.

\*NOTE: Phosphating may be preformed in lieu of sandblasting or in conjunction with the above mechanical etch.

**FINAL CLEAN:** Before spraying the part must be thoroughly cleaned using air blast, hot water rinse, solvent base rinse, or any other method that provides a clean dry surface. DO NOT USE petroleum based solvents,

Test	CXBK
<b>Adhesion</b>	
<b>ASTM D 3330</b>	Pass
<b>Pencil Hardness</b>	8H Plus Pass
<b>Mandrel Bend 1/4" Dia.</b>	Pass
<b>Impact</b>	
<b>ASTM D 2794</b>	Pass
<b>Thermal Resistance</b>	
<b>1200C/2200F Flame</b>	Pass
<b>Thermal Shock Resistance</b>	
<b>540C/1000F Surface *</b>	Pass
<b>Thermal Shock Resistance</b>	
<b>700C/1300F*</b>	Pass
<b>Salt Spray**</b>	Good
<b>Conductivity</b>	Non Conductive
<b>Chemical Soak</b>	Pass
<b>Heated Chemical Quench***</b>	Pass
<b>Color Stability</b>	Pass

THIS INFORMATION IS FURNISHED WITHOUT WARRANTY, REPRESENTATION, INDUCEMENT OR LICENSE OF ANY KIND, EXCEPT THAT IT IS ACCURATE TO THE BEST OF TECH LINE COATINGS, INC., KNOWLEDGE OR OBTAINED FROM SOURCES BELIEVED BY TECH LINE COATINGS INDUSTRIES, INC. TO BE ACCURATE, AND TECH LINE COATINGS INDUSTRIES, INC., DOES NOT ASSUME ANY LEGAL RESPONSIBILITY FOR USE OR RELIANCE UPON SAME. BEFORE USING ANY CHEMICAL, READ ITS LABEL, INSTRUCTIONS AND MATERIAL SAFETY DATA SHEET.